

Santoprene™ 201-87

Thermoplastic Vulcanizate

| Product Description | Key Features |
|---|---|
| A hard, colorable, versatile thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties and chemical resistance for use in a wide range of applications. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding, extrusion, blow molding, thermoforming or vacuum forming. It is polyolefin based and completely recyclable. | <ul style="list-style-type: none"> UL listed: file #QMFZ2.E80017, Plastics - Component; file #QMFZ8.E80017, Plastics Certified For Canada - Component. Recommended for applications requiring excellent flex fatigue resistance. Excellent ozone resistance. EU and China RoHS compliant. |

| General | | | |
|---------------------------|--|---|--|
| Availability ¹ | <ul style="list-style-type: none"> Africa & Middle East Asia Pacific | <ul style="list-style-type: none"> Europe Latin America | <ul style="list-style-type: none"> North America South America |
| Applications | <ul style="list-style-type: none"> Automotive - Boots and Bellows for Steering and Suspension | | |
| Uses | <ul style="list-style-type: none"> Appliance Components Automotive Applications Automotive Under the Hood | <ul style="list-style-type: none"> Consumer Applications Diaphragms Electrical Parts | <ul style="list-style-type: none"> Living Hinges Tubing |
| Agency Ratings | <ul style="list-style-type: none"> EU Annex XVII of Regulation (EC) No 1907/2006 | <ul style="list-style-type: none"> UL QMFZ2 | <ul style="list-style-type: none"> UL QMFZ8 |
| RoHS Compliance | <ul style="list-style-type: none"> RoHS Compliant | | |
| Automotive Specifications | <ul style="list-style-type: none"> CHRYSLER MS-AR100 EGN FORD WSD-M2D382-A1 | <ul style="list-style-type: none"> GM GMP.E/P.005 GM GMW15813, Type 8 | |
| UL File Number | <ul style="list-style-type: none"> E80017 | | |
| Color | <ul style="list-style-type: none"> Natural Color | | |
| Form(s) | <ul style="list-style-type: none"> Pellets | | |
| Processing Method | <ul style="list-style-type: none"> Blow Molding Coextrusion Extrusion Extrusion Blow Molding | <ul style="list-style-type: none"> Injection Blow Molding Injection Molding Multi Injection Molding Profile Extrusion | <ul style="list-style-type: none"> Sheet Extrusion Thermoforming Vacuum Forming |
| Revision Date | <ul style="list-style-type: none"> 11/16/2011 | | |

| Physical | Typical Value (English) | Typical Value (SI) | Test Based On |
|----------------------|-------------------------|-------------------------|---------------|
| Specific Gravity | 0.960 | 0.960 | ASTM D792 |
| Density | 0.960 g/cm ³ | 0.960 g/cm ³ | ISO 1183 |
| Detergent Resistance | f3 | f3 | UL 749 |
| Detergent Resistance | f4 | f4 | UL 2157 |

| Hardness | Typical Value (English) | Typical Value (SI) | Test Based On |
|---|-------------------------|--------------------|---------------|
| Shore Hardness | | | ISO 868 |
| Shore A, 15 sec, 73°F (23°C), 0.0787 in (2.00 mm) | 93 | 93 | |

| Elastomers | Typical Value (English) | Typical Value (SI) | Test Based On |
|--|-------------------------|--------------------|---------------|
| Tensile Stress at 100% - Across Flow (73°F (23°C)) | 1030 psi | 7.10 MPa | ASTM D412 |
| Tensile Stress at 100% - Across Flow (73°F (23°C)) | 1030 psi | 7.10 MPa | ISO 37 |

Typical properties: these are not to be construed as specifications.

©2012 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

ExxonMobil Chemical Santoprene™ 201-87
Thermoplastic Vulcanizate

| Elastomers | Typical Value (English) | Typical Value (SI) | Test Based On |
|---|--------------------------------|---------------------------|----------------------|
| Tensile Strength at Break - Across Flow (73°F (23°C)) | 2550 psi | 17.6 MPa | ASTM D412 |
| Tensile Stress at Break - Across Flow (73°F (23°C)) | 2550 psi | 17.6 MPa | ISO 37 |
| Elongation at Break - Across Flow (73°F (23°C)) | 580 % | 580 % | ASTM D412 |
| Tensile Strain at Break - Across Flow (73°F (23°C)) | 580 % | 580 % | ISO 37 |
| Tear Strength - Across Flow (73°F (23°C), Die C) | 308 lbf/in | 54.0 kN/m | ASTM D624 |
| Tear Strength - Across Flow 73°F (23°C), Method Bb, Angle (Nicked) | 310 lbf/in | 54 kN/m | ISO 34-1 |
| Compression Set 158°F (70°C), 22.0 hr, Type 1 | 36 % | 36 % | ASTM D395B |
| 257°F (125°C), 70.0 hr, Type 1 | 44 % | 44 % | |
| Compression Set 158°F (70°C), 22.0 hr, Type A | 36 % | 36 % | ISO 815 |
| 257°F (125°C), 70.0 hr, Type A | 44 % | 44 % | |
| Thermal | Typical Value (English) | Typical Value (SI) | Test Based On |
| Brittleness Temperature | -65 °F | -54 °C | ASTM D746 |
| Brittleness Temperature | -65 °F | -54 °C | ISO 812 |
| RTI Elec | 212 °F | 100 °C | UL 746 |
| RTI Str 0.0394 in (1.00 mm) | 194 °F | 90.0 °C | UL 746 |
| 0.0591 in (1.50 mm) | 194 °F | 90.0 °C | |
| 0.118 in (3.00 mm) | 203 °F | 95.0 °C | |
| Electrical | Typical Value (English) | Typical Value (SI) | Test Based On |
| Dielectric Strength 73°F (23°C), 0.0800 in (2.03 mm) | 820 V/mil | 32 kV/mm | ASTM D149 |
| Dielectric Constant 73°F (23°C), 0.0780 in (1.98 mm) | 2.40 | 2.40 | ASTM D150 |
| Dielectric Constant 73°F (23°C), 0.0780 in (1.98 mm) | 2.40 | 2.40 | IEC 60250 |
| Comparative Tracking Index (CTI) | PLC 0 | PLC 0 | UL 746 |
| High Amp Arc Ignition (HAI) | PLC 0 | PLC 0 | UL 746 |
| High Voltage Arc Resistance to Ignition (HVAR) | PLC 5 | PLC 5 | UL 746 |
| High Voltage Arc Tracking Rate (HVTR) | PLC 1 | PLC 1 | UL 746 |
| Hot-wire Ignition (HWI) 0.0394 in (1.00 mm) | PLC 4 | PLC 4 | UL 746 |
| 0.0591 in (1.50 mm) | PLC 3 | PLC 3 | |
| 0.118 in (3.00 mm) | PLC 2 | PLC 2 | |
| Injection | Typical Value (English) | Typical Value (SI) | |
| Drying Temperature | 180 °F | 82.2 °C | |
| Drying Time | 3.0 hr | 3.0 hr | |
| Suggested Max Moisture | 0.080 % | 0.080 % | |

Typical properties: these are not to be construed as specifications.

©2012 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

**ExxonMobil Chemical Santoprene™ 201-87
Thermoplastic Vulcanizate**

| Injection | Typical Value (English) | Typical Value (SI) |
|-------------------------|---------------------------------|-------------------------|
| Suggested Max Regrind | 20 % | 20 % |
| Rear Temperature | 360 °F | 182 °C |
| Middle Temperature | 370 °F | 188 °C |
| Front Temperature | 380 °F | 193 °C |
| Nozzle Temperature | 390 to 455 °F | 199 to 235 °C |
| Processing (Melt) Temp | 400 to 450 °F | 204 to 232 °C |
| Mold Temperature | 50.0 to 125 °F | 10.0 to 51.7 °C |
| Injection Rate | Fast | Fast |
| Back Pressure | 50.0 to 100 psi | 0.345 to 0.689 MPa |
| Screw Speed | 100 to 200 rpm | 100 to 200 rpm |
| Clamp Tonnage | 3.0 to 5.0 tons/in ² | 41 to 69 MPa |
| Cushion | 0.125 to 0.250 in | 3.18 to 6.35 mm |
| Screw L/D Ratio | 16.0:1.0 to 20.0:1.0 | 16.0:1.0 to 20.0:1.0 |
| Screw Compression Ratio | 2.0:1.0 to 2.5:1.0 | 2.0:1.0 to 2.5:1.0 |
| Vent Depth | 0.0010 in | 0.025 mm |

Injection Notes

Santoprene TPV is incompatible with acetal and PVC. For more information regarding processing and mold design, please consult our Injection Molding Guide.

| Extrusion | Typical Value (English) | Typical Value (SI) |
|--------------------|-------------------------|--------------------|
| Drying Temperature | 180 °F | 82.2 °C |
| Drying Time | 3.0 hr | 3.0 hr |
| Melt Temperature | 400 °F | 204 °C |
| Die Temperature | 410 °F | 210 °C |
| Back Pressure | 725 to 2900 psi | 5.00 to 20.0 MPa |

Extrusion Notes

Santoprene TPV is incompatible with acetal and PVC. For more information regarding processing and mold design, please consult our Extrusion Guide.

| Aging | Typical Value (English) | Typical Value (SI) | Test Based On |
|---|-------------------------|--------------------|---------------|
| Change in Tensile Strength in Air 302°F (150°C), 168 hr | -15 % | -15 % | ASTM D573 |
| Change in Tensile Strength in Air 302°F (150°C), 168 hr | -15 % | -15 % | ISO 188 |
| Change in Ultimate Elongation in Air 302°F (150°C), 168 hr | -16 % | -16 % | ASTM D573 |
| Change in Tensile Strain at Break in Air 302°F (150°C), 168 hr | -16 % | -16 % | ISO 188 |
| Change in Durometer Hardness in Air Shore A, 302°F (150°C), 168 hr | 2.0 | 2.0 | ASTM D573 |
| Change in Shore Hardness in Air Shore A, 302°F (150°C), 168 hr | 2.0 | 2.0 | ISO 188 |
| Continuous Upper Temperature Resistance | 275 °F | 135 °C | SAE J2236 |

Typical properties: these are not to be construed as specifications.

©2012 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

ExxonMobil Chemical Santoprene™ 201-87 Thermoplastic Vulcanizate

| Flammability | Typical Value (English) | Typical Value (SI) | Test Based On |
|---------------------|-------------------------|--------------------|---------------|
| Flame Rating | | | UL 94 |
| 0.0394 in (1.00 mm) | HB | HB | |
| 0.0591 in (1.50 mm) | HB | HB | |
| 0.118 in (3.00 mm) | HB | HB | |

Additional Information

Values are for injection molded plaques, fan-gated, 102.0 mm x 152.0 mm x 2.0 mm (4.000" x 6.000" x 0.080").
Tensile strength, elongation and tensile stress are measured across the flow direction - ISO type 1, ASTM die C.
Compression set at 25% deflection.

Legal Statement

For detailed Product Stewardship information, please contact Customer Service.

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use.

Processing Statement

Desiccant drying for 3 hours at 80°C (180°F) is recommended. Santoprene TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC. For more information, please consult our Material Safety Data Sheet, Injection Molding Guide and Extrusion Guide.

Notes

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance:

Worldwide and the Americas

ExxonMobil Chemical Company
13501 Katy Freeway
Houston, TX 77079-1398
USA
1-281-870-6050

Asia Pacific

ExxonMobil Chemical Asia Pacific
1 HarbourFront Place
#06-00 HarbourFront Tower One
Singapore 098633
+86-21-24173999

Europe, Middle East and Africa

ExxonMobil Chemical Europe
Hermeslaan 2
1831 Machelen, Belgium
420-239-016-274

Typical properties: these are not to be construed as specifications.

©2012 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.