

Technical Datasheet

DESCRIPTION

Novodur HH-112 is a high heat injection molding grade. It provides extraordinary heat resistance combined with enhanced stiffness.

FEATURES

- Very high heat resistance
- High stiffness

APPLICATIONS

- Automotive rear lamp housings
- Glove box caps

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm ³ /10 min	6
Melt Volume Rate, 200 °C/21,6 kg MVR	ISO 1133	cm ³ /10mi	6
Mechanical Properties			
Charpy Notched Impact Strength, 23° C	ISO 179	kJ/m ²	12
Charpy Notched Impact Strength, -30° C	ISO 179	kJ/m ²	5
Charpy Unnotched, 23° C	ISO 179	kJ/m ²	140
Charpy Unnotched, -30° C	ISO 179	kJ/m ²	80
Tensile stress at yield, 23° C	ISO 527	MPa	58
Tensile strain at yield, 23° C	ISO 527	%	3.1
Tensile Modulus	ISO 527	MPa	2700
Elongation at Break (MD)		%	8
Flexural Strength	ISO 178	MPa	81
Ball Indentation Hardness	ISO 2039-1	MPa	114
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50°C/h, 50N)	ISO 306	°C	112
Vicat Softening Temperature, VST/A/50 (50°C/h, 10N)	ISO 306	°C	118
Heat Deflection Temperature; (annealed) method Af, 1.8 MPa	ISO 75	°C	109
Heat Deflection Temperature; (annealed) method Bf, 0.45 MPa	ISO 75	°C	113
Linear Mold Shrinkage	ISO 294-4	%	0.4 - 0.7
Coefficient of Linear Thermal Expansion	ISO 11359	10-6/°C	70 - 110

Property, Test Condition	Standard	Unit	Values
Thermal conductivity	DIN 52612-1	W/(m K)	0.17
Electrical Properties			
Volume Resistivity	IEC 60093	Ohm*m	1E13
Other Properties			
Density	ISO 1183	kg/m ³	1050
Moisture, 50% RH	ISO 62	%	0.25
Processing			
Processing (Melt) Temperature	ISO 294	°C	230 - 270
Mold Temperature	ISO 294	°C	40 - 60
Injection velocity	ISO 294	mm/s	200
Drying Temperature		°C	80
Drying Time		hr	2 - 4
Max service temperature		°C	90

Typical values for uncolored products

SUPPLY FORM

Novodur® is delivered in the form of cylindrical or spherical pellets. The bulk density of the pellets is from 0.55 to 0.65 g/cm³. Values may differ for special grades. Standard Packaging unit: 25 kg PE-bag on palette, shrunk or wrapped with PE film. In addition, delivery in larger units of up to 1000 kg (IBC = Intermediate Bulk Container) or silo trucks can be arranged. In dry areas with normal temperature control, Novodur pellets can be stored for relatively long periods of time without any change in mechanical properties. With unstable colors, however, storage over a number of years can give rise to some change in color. Under poor storage conditions, Novodur absorbs moisture, but this can be removed by drying.

PRODUCT SAFETY

No adverse effects on the health of processing personnel have been observed where the products are correctly processed and the production areas are suitably ventilated. For styrene, alpha-methylstyrene, acrylonitrile, and butyl acrylate the maximum allowable workplace concentrations must be observed according to the pertaining national regulations. In Germany, the following limit values are valid TRGS 900 (Aug. 2004): styrene, MAK-value: 20 ml/m³; alpha-methylstyrene, MAK-value: 100 ml/m³; acrylonitrile, TRK-value: 3 ml/m³, and butyl acrylate, MAK-value: 2 ml/m³ (1.7.2004). According to EU directive 67/548/EEC, Annex I (2001), acrylonitrile is classified as carcinogenic, category 2 ('substances which should be regarded as if they are carcinogenic to man'). Experience has shown that when Novodur® is processed correctly with appropriate ventilation, the levels are far below the limits mentioned above. Inhalation of the vapors of degradation products which can arise on severe overheating of the materials or during purging out should be avoided. Further information can be found in the Novodur safety data sheets.

DISCLAIMER

The above information is provided in good faith. Styrolution is not responsible for any processing or compounding which may occur to product finished articles, packaging materials or their components. Further, Styrolution MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN OR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.